

Permit Number: EPR/BL3986ID

Operator: Tarmac Cement and
limeLtd

Installation: Aberthaw Works

Form number: Fuel 1 / 31 August 2010

Reporting of Fuel Usage for the Cement Kiln for the month January 2020

Fuel	Quantity burned Tonnes	Average calorific value MJ/kg
Coal	4288.0	25.70
Petroleum coke		
Distillate fuel oil	83.0	43.89
MBM		
Tyres	562.0	27.87
SRF 1	574.0	19.14
Polychip	236.0	33.77
Relative thermal input of waste derived fuels		
MBM		0%
Tyres		11%
SRF		7%
Polychip		5%

Signed: Georgina Taubman, HSE Officer (georgina.taubman@tarmac.com)
(authorised to sign as representative of Lafarge Tarmac Cement and Lime Ltd)
Date: 8.4.2020

Permit Number: EPR/BL3986ID

Operator: Lafarge Tarmac Cement
and lime Ltd

Installation: Aberthaw Works

Form number: Fuel 1 / 31 August 2010

Reporting of Fuel Usage for the Cement Kiln for the month February 2020

Fuel	Quantity burned Tonnes	Average calorific value MJ/kg
Coal	1154.0	26.14
Petroleum coke		
Distillate fuel oil	0.0	0.00
Tyre Fluff	15.0	34.41
Tyres	259.0	27.87
SRF 1	273.0	19.14
Polychip	4.0	33.77
Relative thermal input of waste derived fuels		
Tyre Fluff		1%
Tyres		17%
SRF		12%
Polychip		0%

Signed: Georgina Taubman, HSE Officer (georgina.taubman@tarmac.com)
(authorised to sign as representative of Lafarge Tarmac Cement and Lime Ltd)
Date: 8.4.2020

Permit Number: EPR/BL3986ID

Operator: Lafarge Tarmac Cement
and lime Ltd

Installation: Aberthaw Works

Form number: Fuel 1 / 31 August 2010

Reporting of Fuel Usage for the Cement Kiln for the month March 2020

Fuel	Quantity burned Tonnes	Average calorific value MJ/kg
Coal	3151.0	26.79
Petroleum coke		
Distillate fuel oil	112.0	43.89
MBM		
Tyres	554.6	27.87
SRF 1	434.2	19.14
Polychip	125.7	33.77
Relative thermal input of waste derived fuels		
MBM		0%
Tyres		13%
SRF		7%
Polychip		4%

Signed: Georgina Taubman, HSE Officer (georgina.taubman@tarmac.com)
(authorised to sign as representative of Lafarge Tarmac Cement and Lime Ltd)
Date: 8.4.2020