

Permit Number: EPR/BL3986ID

Operator: Lafarge Tarmac Cement and lime Ltd

Installation: Aberthaw Works

Form number: Fuel 1 / 31 August 2010

Reporting of Fuel Usage for the Cement Kiln for the month Oct 2014

Fuel	Quantity burned Tonnes	Average calorific value MJ/kg
Coal	4472.7	27.66
Petroleum coke		
Distillate fuel oil	3.1	43.20
MBM		
Tyres	847.6	29.50
SRF 1	112.6	35.05
SRF 2	987.7	15.47
Relative thermal input of waste derived fuels		
MBM	0.0%	
Tyres	14.9%	
SRF	11.4%	

Signed: Robert Fairless, Environment Coordinator (via robert.fairless@lafargetarmac.com)

(authorised to sign as representative of Lafarge Tarmac Cement and Lime Ltd)

Date: 19/11/2014